



DPR Coating Acrylic Coating



DESCRIPTION:

- 100% Acrylic-based coating
- **DPR (Dirt Pick-up Resistance):** The surface of the coating hardens and does not soften again under heat. The non-tacky surface provides high resistance to accumulation of dirt, mold, and pollutants
- Excellent hiding power as well as flexibility and drying characteristics
- Integrally colored with high quality pigments

USES:

- A protective and decorative exterior or interior coating over concrete, masonry, stucco, or acrylic-based textured finishes. Compatible with LaHabra finishes may be applied over them.
- To promote color uniformity of repaired and modified surfaces
- To color architectural details and graphics on any of the LaHabra Finishes and Coatings.
- Recoating existing EIFS

COMPOSITION:

- Binder Base: 100% Acrylic
- Color: White or tinted to desired color
- Pigment based: Titanium Dioxide
- Solids:
 - By weight: 58%
 - By volume: 48%
- Water base: VOC-Compliant

PROPERTIES:

- Appearance: Flat, non-gloss, smooth finish
- Vapor Permeability: Water vapor permeable. Does not create a vapor barrier

COVERAGE:

Depending on the condition of the substrate and method of application, approximate coverages are:

DPR Coating
One coat: 1000-1200 ft²
(93-112 m²) / pail

CONTAINER:

- 60 lb (27.2 kg) net weight in plastic pails.
- **Storage:** Protect from direct sunlight and freezing at all times
 - Do not stack pails more than 3 pails high
 - **Shelf Life:** One year if properly stored in original unopened container.

DRYING TIME:

Approximately 1-4 hours depending upon temperature, humidity and substrate. Can be recoated after 8 hours. Allow minimum 5 days curing before gently washing the surface.

CLEAN-UP:

Water soluble prior to drying. Clean tools and containers with water prior to drying.

SURFACE PREPARATION:

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- For previously painted surfaces, all loose and chalking paint must be removed and glossy surfaces dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days.
- Check concrete surfaces for alkalinity and treat. Any form-release agents or bond breakers must be removed.
- Uneven concrete or masonry can be leveled with Level Coat, LaHabra Polybond, LaHabra Fastwall Stucco Base all or other suitable, compatible product.
- For interior drywall, prepare as for painting.

- Prime cementitious surfaces with LaHabra Acrylic Primer.
- For application of LaHabra Acrylic Primer refer to the Product Data Sheet.
- For additional options, contact Parex USA Technical Support.

MIXING:

- Use clean equipment for mixing and preparation
- Stir LaHabra DPR Coating to a uniform consistency.
- Avoid creating air bubbles or foam.
- Stir occasionally as needed to keep uniformly mixed.

APPLICATION:

- Read the entire label before using this product
- LaHabra DPR Coating exhibits good surface coverage in single application. However, for most uncoated, unprimed surface of concrete, masonry, or drywall, two coats of the product may be required to obtain adequate hiding of the substrate and best performance.
- LaHabra DPR Coating is easily applied with either brush, roller, or suitable spray equipment. Apply as packaged. If necessary, add a small amount of clean potable water: maximum 8 oz (0.25L) / pail.
- Add the same amount of water to each bucket. Also if different batches are used on the job box them for best color consistency. For more information see Technical Bulletin: "Boxing Acrylic Finishes"

LIMITATIONS:

- Ambient and surface temperatures must be 40°F (4.4°C) or higher during application and drying time. Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, and free from any residue which may affect the ability of either the LaHabra DPR Coating to bond to the surface.
- Application in direct sunlight in hot weather may adversely affect aesthetics.



Corporate Office

Parex USA, Inc.
4125 E. La Palma Ave., Suite 250
Anaheim, CA 92807
(866) 516-0061
Tech Support: (800) 226-2424

Facilities

Riverside, CA
French Camp, CA
Albuquerque, NM
Colorado Springs, CO
Anaheim, CA

North Hollywood, CA
San Antonio, TX
Redan, GA
Wilkes Barre, PA

